

## NITgold Cit 30nm

**STORE AT 4°C away from light. DO NOT FREEZE**

### Description

---

The 30nm gold nanoparticles are uniform quasi-spherical gold nanoparticles with a mean diameter of thirty nanometers capped with citrate. These nanoparticles present unique physico-chemical properties (i.e. optical, catalytic, electrochemical activity, etc.). Citrate gold nanoparticles are excellent candidates to be functionalized since a wide range of molecules can be tethered onto the AuNP surface by means of a thiol (SH) group displacing adsorbed citrate anions. Once functionalized, they can be employed as platforms for many applications such as target-specific drug delivery, sensors, lateral flow tests, imaging probes for dark-field microscopy, flow cytometry, cancer photothermal therapy, catalysis, and optoelectronic. They can be also conjugated with distinct molecules and/or other micro/nanostructures to generate new biosensors, therapeutics, etc. The optical and electronic properties of gold nanoparticles are tuneable by changing their size, shape, surface chemistry or even their aggregation state.

### Technical Specifications

---

<b>Particle Surface:</b> Citrate capping	<b>Peak SPR wavelength:</b> 526 ± 2 nm
<b>Average Diameter:</b> <sup>1</sup> 29.3 ± 3.5 nm	<b>Hydrodynamic Diameter (DLS):</b> 30.1 ± 3.2 nm
<b>Molar Concentration:</b> <sup>2</sup> 0.28 nM	<b>O.D.:</b> 1
<b>Particle Concentration:</b> 1.7×10 <sup>11</sup> particles/mL	<b>Z-Potential:</b> -36.2 mV
<b>Solvent:</b> Milli-Q Water	<b>pH of Solution:</b> 5.0


---

<sup>1</sup> Particle diameter determined by Surface Plasmon Resonance from the spectrum. Haiss et al. Anal. Chem. 2007, 79, 4215-4221.


<sup>2</sup> Determined according to a  $\epsilon = 3.52 \times 10^9 \text{ M}^{-1} \cdot \text{cm}^{-1}$ . Werts et al. Analyst 2013, 138, 583-592.



**UV/visible absorbance spectrum**



**Size Distribution (DLS)**



**Suggested Application(s)<sup>1</sup>**

- Biosensing
- Catalysis
- Drug delivery
- Colorimetric probes
- Lateral flow immunoassays

**Ordering Information**

Product name	Nanoparticles/mL	O.D.	$\epsilon$ (M <sup>-1</sup> cm <sup>-1</sup> )	Quantity	Catalogue ref.
NITgold Cit 30nm - 1 OD	3.12E+11	1	1.93E+09	25 mL	51001017V
NITgold Cit 30nm - 1 OD	3.12E+11	1	1.93E+09	100 mL	510010160
NITgold Cit 30nm - 1 OD	3.12E+11	1	1.93E+09	250 mL	51001016C
NITgold Cit 30nm - 1 OD	3.12E+11	1	1.93E+09	500 mL	51001016F
NITgold Cit 30nm - 3 OD	9.37E+11	3	1.93E+09	25 mL	51001117V
NITgold Cit 30nm - 3 OD	9.37E+11	3	1.93E+09	100 mL	510011160
NITgold Cit 30nm - 3 OD	9.37E+11	3	1.93E+09	250 mL	51001116C



Order by Email: [sales@nanoimmunotech.es](mailto:sales@nanoimmunotech.es)

**Product disclaimer**

This nanoparticles product is to be used for research purposes only. Unless stated in the documentation of on an individual product label, catalogue or other information provided to the buyer, IT IS FORBIDDEN TO USE IT for different purposes, including but not limited to them: in vitro diagnostic, use in food, pharmaceutical purposes, medical purposes, or use in cosmetic products, neither for use in humans nor animals, nor for any commercial purposes. Please refer to [www.nanoimmunotech.eu](http://www.nanoimmunotech.eu) for the Material Safety Data Sheet of the product.

The information given in this document is to the best of our knowledge.

<sup>1</sup>Since conditions of use are beyond our control, we do not warranty the suitability of our products.

